



## AC-®665 Class B Corrosion Inhibitive Sealant

SIN #834-100

### Description

AC-®665 Class B is a two-part, manganese-cured, chromated, corrosion inhibiting sealant. This sealant provides an effective barrier against the common causes of corrosion on aluminum and between dissimilar metals. AC-®665 Class B has outstanding resistance to aviation gasoline and jet fuel, as well as resistance to chemicals, hydraulic fluids and petroleum products common to the aircraft industry. The mixed compound is a thixotropic paste, easily applied by spatula, extrusion gun or injection gun. It maintains its flexibility and bond strength on most metal substrates under extremes of temperature, weathering and stress.

### Applications

- sealing faying surfaces of mating parts
- sealing joints from passage of liquid or air
- prevent corrosion and channeling leakage

### Specifications

BAMS 552-007	Qualified B-1/2, B-2
CML 09-044	Qualified B-1/2, B-2
GAMPS 7115	Qualified B-1/2, B-2
MB1658	Qualified B-1/2, B-2
MIL-PRF-81733	Qualified B-1/2, B-2
STM 40-111	Qualified
299-947-074	B-2 (PMF) Qualified

### Typical Physical and Application Properties

Color	
Base:	Yellow
Accelerator:	Black
Mixing Ratio	100 base/10 accelerator (by weight)
Nonvolatile Content	98%
Base Viscosity (RVF Brookfield #7 spindle @ 2 rpm, 77°F)	6,000-9,000 poise

### Application Life and Cure Time (@ 75°F, 50% Relative Humidity)

	Minimum Application Life <sup>1</sup>	Typical Tack-Free Time <sup>2</sup>	Typical Cure Time <sup>3</sup>
B-1/2	½ hours	6 hours	12 hours
B-2	2 hours	20 hours	60 hours

### Typical Physical and Performance Properties of Cured Compound when tested per STM 40-111 and MIL-PRF-81733

Color	Black
Specific Gravity	1.60
Hardness	52 Shore "A"
Low Temperature Flexibility	No cracking, checking or adhesion loss when tested at -65°F (-54°C)
Thermal Stability, 48 hrs @ 200°F	Does not soften, blister, crack or blow
Service Temperatures	-65° to +250°F (-54° to +121°C)
Tensile Strength	250 psi
Elongation	425%
Corrosion	Excellent protection from corrosion caused by galvanic coupling of dissimilar metals
Soluble Chromate Content	4-5%
Repairability	35-piw/100% cohesive to itself and other STM 40-111 and MIL-PRF-81733 qualified sealants
Fungus Resistance	Non-nutrient

<sup>1</sup> Application life refers to the length of time the mixed compound remains at a consistency suitable for application with spatula or caulking gun. Application life is measured at a standard temperature of 77°F and a relative humidity level of 50%. In general, for every 20°F rise in temperature, the application life is halved; and for every 20°F drop, it is doubled. High humidity levels during the mixing process will shorten application life.

<sup>2</sup> Tack-free time is the length of time after which a mixed sealant will no longer tightly adhere to L-LP-690 standard low density polyethylene film.

<sup>3</sup> Cure time is defined as the length of time it takes AC-665 Class B sealant to reach 30A hardness. It depends on three factors: remaining application life, temperature and relative humidity. The temperature/humidity factors for application life also apply to curing. High humidity during cure will speed up the cure. To accelerate the curing process, apply heat up to (but not more than) 140°F.

## Peel Strength\*

Substrate	Conditioning	Load/% Cohesion
Mil-C-81706	Dry	47 lbs./100%
Mil-C-81706	3% NaCl, 48 hours @ 140°F	53 lbs./100%
Mil-C-81706	JRF 48 hours @ 140°F	34 lbs./100%
Mil-A-8625	Dry	52 lbs./100%
Mil-A-8625	3% NaCl, 48 hours @ 140°F	53 lbs./100%
Mil-A-8625	JRF 48 hours @ 140°F	33 lbs./100%
Mil-T-9046	Dry	49 lbs./100%
Mil-T-9046	3% NaCl, 48 hours @ 140°F	50 lbs./100%
Mil-T-9046	JRF 48 hours @ 140°F	36 lbs./100%
QQ-P-416 TyII <sup>1</sup>	Dry	51 lbs./100%
QQ-P-416 TyII <sup>1</sup>	3% NaCl, 48 hours @ 140°F	52 lbs./100%
QQ-P-416 TyII <sup>1</sup>	JRF 48 hours @ 140°F	36 lbs./100%

\*Tested per Mil-PRF-81733D

Specification requirement: 15-piw/100% cohesive failure

<sup>1</sup> Primed with AMS-3100 adhesion promoter

### Two-Part Sealant Cartridges:

1. Holding the cartridge, grasp the dasher rod and pull back approximately one inch.
2. Insert the ramrod into the hollow of the dasher rod, break the piston loose, and inject about 1/3 of the contents into the cartridge.

*Note: Do not inject all of catalyst in one location. Distribute evenly throughout base material.*

3. Repeat steps 2 and 3 until all the contents of the rod are emptied into the cartridge. Remove the ramrod.
4. Mix for the required number of strokes (hand mixing) or for the required amount of time (machine mixing) indicated in the kit instructions.

5. When mixing is complete, remove bottom cap.
6. Pull the dasher rod back to the neck of the cartridge, grasp the cartridge firmly at the neck, unscrew the dasher rod and remove.
7. Screw the nozzle into the cartridge, insert into the extrusion gun and use as required. For hand extrusion, press the used dasher rod against the plunger to force the material from the cartridge.

### Storage

The shelf life of AC-<sup>®</sup>665, Class B sealant is at least 9 months from date of packaging, when stored at temperatures below 80°F in its original container.

Mixed AC-<sup>®</sup>665 Class B may be stored under refrigeration as follows:

15 days at -10°F

30 days at -40°F

It is important to remember that freezing, storing and thawing procedures reduce application life. Also, frozen storage will reduce application life by varying amounts depending on the storage temperature and length of storage time. All aspects of storage, freezing and thawing should be planned carefully and it is not recommended to mix and freeze with less than ½ hour application time.

### Health and Safety Precautions

AC-<sup>®</sup>665 Class B sealant is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Material Safety Data Sheet (MSDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An MSDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

All values are typical and are not intended for specification use.

AC- and AC TECH are trademarks of Advanced Chemistry & Technology, Inc. registered with the US Patent and Trademark Office

US Patent 6,486,268

AC-665B-01/08

*Seller and manufacturer make no warranty, express or implied, concerning this product, or its merchantability or fitness for any purpose, except that the product conforms to manufacturer's product specifications during its applicable shelf life. User shall determine the suitability of this product for the intended purpose and method of application. Seller and manufacturer's only obligation shall be to replace the quantity of the product proved to be defective. AC TECH shall not be liable for damages in excess of the purchase price of this product.*