



# AC-<sup>®</sup>236 Class B Fuel Tank and Fuselage Sealant

SIN #834-100

## Description

AC-<sup>®</sup>236 Class B is a two-component, manganese dioxide cured, liquid polysulfide polymer system providing excellent fuel tank and fuselage seals. It has outstanding resistance to aviation gasoline and jet fuel, as well as resistance to chemicals and petroleum products common to the aircraft industry. AC-<sup>®</sup>236 Class B maintains its flexibility and bond strength on most metal substrates like aluminum, stainless steel, steel, and many coatings under extremes of temperature, weathering and stress. The mixed compound is a thixotropic paste easily applied by extrusion, injection gun or spatula. It has excellent tooling properties.

## Applications

- Sealing integral fuel tanks
- Repairing integral fuel tanks
- Sealing fuselages

## Specifications

AMS-S-8802	Qualified
FMS 1049	Qualified
299-947-074	Qualified
LES 1039 BU	Qualified
HS 12373 Rev A	Qualified
BS 25146	Qualified
WL 5.5902	Meets Requirements
DTD 900/6147	Meets Requirements
STRYP 5960	Meets Requirements

## Typical Physical and Application Properties

Color	
Base:	White
Accelerator:	Black
Mix Ratio	100 base/10 accelerator (by weight)
Nonvolatile Content	97%
Base Viscosity (RVF Brookfield #7 spindle @ 2rpm, 77°F)	9,000-14,000 poise

Accelerator Viscosity  
(RVF Brookfield #7 spindle  
@ 10rpm, 77°F) 700-1600 poise

## Application Life and Cure Time (@ 77°F, 50% Relative Humidity)

	Minimum Application Life <sup>1</sup>	Typical Tack-Free Time <sup>2</sup>	Typical Cure Time <sup>3</sup>
B-1/2	1/2 hour	8 hours	24 hours
B-2	2 hours	24 hours	48 hours
B-4	4 hours	36 hours	90 hours

## Typical Physical and Performance Properties of Cured Compound after 14 Days @ 77°F/50% RH when tested per AMS-S-8802

Color	Gray
Specific Gravity	1.64
Hardness	60 Shore "A"
Low Temperature Flexibility	No cracking, checking or adhesion loss when tested at -65°F (-54°C)
Service Temperatures	-65° to +250°F (-54° to +121°C)
Thermal Rupture	
Resistance Corrosion	Does not blister or sponge. None.
Fuel Resistance	70 days at 140°F, 35 piw/100% cohesive failure.
Repairability	40 piw to itself and other AMS-S-8802 qualified sealants.
Resistance to Other Fluids	No cracking when bent 180° over a 1/8 inch mandrel. No more than 6% loss of the sealant compound after fluid immersion

<sup>1</sup>Application life refers to the length of time that mixed compound remains at a consistency suitable for application with spatula or caulking gun. Application life is always measured at a standard temperature of 77°F with a relative humidity level of 50%. In general, for every 20°F rise in temperature, the application life is halved; and for every 20°F drop, it is doubled. High humidity levels during the mixing process will shorten application life.

<sup>2</sup>Tack-free time is the length of time after which a mixed sealant will no longer tightly adhere to L-LP-690 standard low density polyethylene film.

<sup>3</sup>Cure time is defined as the length of time it takes AC-236 Class B sealant to reach 30A hardness. It depends on three factors: remaining application life, temperature and relative humidity. To a certain extent, the temperature/humidity factors for application life also apply to curing. To accelerate the curing process, apply heat up to (but not more than) 120°F.



## Typical Values of AC-<sup>®</sup>236 Class B to AMS-S-8802

### Tensile Strength and % Elongation

Conditioning	Specification Requirements	Results
Standard Cure--14 days	200 psi/200%	350psi/220%
JRF-14 days @ 140°F	50 psi/200%	215psi/210%
7 days @ 250°F	125 psi/100%	315psi/240%
JRF-72 hrs @ 140°F, and Air Drying-72 hours @ 120°F, and 7 days @ 250°F	200 psi/75%	360psi/195%
24 hrs @ 250°F, and JRF-7 days @ 140°F	100 psi/150%	240psi/175%

### Peel Strength\*\*

Substrate	Conditioning	Load / % Cohesion
MIL-C-5541	7 days @ 140°F in JRF	55lbs./100%
	7 days @ 140°F in JRF/SW	50lbs./100%
AMS 2471 Anodized	7 days @ 140°F in JRF	52lbs./100%
	7 days @ 140°F in JRF/SW	45lbs./100%
MIL-C-27725	7 days @ 140°F in JRF	50lbs./100%
	7 days @ 140°F in JRF/SW	56lbs./100%
MIL-P-23377	7 days @ 140°F in DI Water	51lbs./100%
	7 days @ 140°F in SW	53lbs./100%
Stainless Steel	7 days @ 140°F in JRF	46lbs./100%
	7 days @ 140°F in JRF/SW	48lbs./100%
Graphite Epoxy AS 4/3501-6	7 days @ 140°F in JRF	42lbs./100%
	7 days @ 140°F in JRF/SW	44lbs./100%

\*\* Specification requirement - 20-lbs./100%, wire mesh

### Two Part Sealant Cartridges:

1. Holding the cartridge, grasp the dasher rod and pull back approximately one inch.
2. Insert the ramrod into the hollow of the dasher rod, break the piston loose, and inject about 1/3 of the contents into the

cartridge.

*Note: Do not inject all of catalyst in one location. Distribute evenly throughout base material.*

3. Repeat steps 2 and 3 until all the contents of the rod are emptied into the cartridge. Remove the ramrod.
4. Mix for the required number of strokes (hand mixing) or for the required amount of time (machine mixing) indicated in the kit instructions.
5. When mixing is complete, remove bottom cap.
6. Pull the dasher rod back to the neck of the cartridge, grasp the cartridge firmly at the neck, unscrew the dasher rod and remove.
7. Screw the nozzle into the cartridge, insert into the extrusion gun and use as required. For hand extrusion, press the used dasher rod against the plunger to force the material from the cartridge.

### Storage

The shelf life of AC-<sup>®</sup>236 Class B is 9 months from date of packaging, when stored at temperatures below 80°F in its original container.

Mixed AC-<sup>®</sup>236 Class B may be stored under refrigeration as follows:

15 days at -10°F  
30 days at -40°F

It is important to remember that freezing, storing and thawing procedures reduce application life. Also, frozen storage will reduce application life by varying amounts depending on the storage temperature and length of storage time. All aspects of storage, freezing and thawing should be planned carefully and it is not recommended to mix and freeze with less than 1/2-hour application time.

### Health and Safety Precautions

AC-<sup>®</sup>236 Class B sealant is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Material Safety Data Sheet (MSDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An MSDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure

All values are typical and are not intended for specification use.

AC- and AC TECH are trademarks of Advanced Chemistry & Technology, Inc. registered with the US Patent and Trademark Office  
US Patent 6,486,268

**AC-236B-01/09**

*Seller and manufacturer make no warranty, express or implied, concerning this product, or its merchantability or fitness for any purpose, except that the product conforms to manufacturer's product specifications during its applicable shelf life. User shall determine the suitability of this product for the intended purpose and method of application. Seller and manufacturer's only obligation shall be to replace the quantity of the product proved to be defective. AC TECH shall not be liable for damages in excess of the purchase price of this product.*

Advanced Chemistry & Technology, Inc