



AC-[®]615 Class B Low Adhesion Access Door Sealant Chromated

SIN #834-100

Description

AC-[®]615 Class B is a two-part, low adhesion, chromate containing, corrosion inhibiting polysulfide access door sealant for faying surfaces where easy separation of joined surfaces is required. It compounds into a highly thixotropic reddish paste which can easily be applied with a spatula, putty knife or caulking gun. The cured AC-[®]615 sealant has low adhesion and forms a tough, "rubbery" gasket that molds to surface irregularities.

Applications

- Access door sealant for aerospace metallic structure and pressurized vehicles
- Gaskets for removable parts
- Strippable fillets

Specifications

AMS 3267 - GSA Approved
TAPS 1163 Ty IV - Qualified

Typical Physical and Application Properties

Color	
Base:	Red
Accelerator:	Black
Mixed:	Dark Red
Mixing Ratio	100 base / 10 accelerator (by weight)
Non-Volatile Content	97%
Base Viscosity (Brookfield #7 spindle @ 2 rpm)	9,000 to 11,000 poise
Vertical Flow	0.2 inches

Application Life and Cure Time

(@ 75°F, 50% Relative Humidity)

	Minimum Application Life ¹	Typical Tack-Free Time ²	Typical Cure Time ³
B-1/2	½ hour	6 hours	8 hours
B-2	2 hours	20 hours	26 hours

Typical Physical and Performance Properties of Cured Compound

Color	Red
Specific Gravity	1.53
Hardness	45 Shore "A"
Adhesion to Aluminum steel, stainless steel, titanium, zinc, cadmium, chromium, magnesium, glass, enamel, Epoxy MIL-P-23377 and Urethane MIL-C-27725	≤ 3 lb./in of width positive adhesion
Ultimate Elongation	200%
Temperature Range	-65°F to +200°F
Low Temperature Flexibility	-65°F (-54°C)
Fuel Resistance	4.5% weight loss after 7 days at 140°F in TT-S-735, Type III fuel.
TT-S-735, Type VII	5.5% weight loss after 9 days at 140°F in Type VII Fuel
Resistance to Other Fluids	Excellent resistance to water, alcohols, petroleum and synthetic lubricating oils and petroleum-base hydraulic fluids
Effect on Acrylic Plastics	Will not cause crazing
Fungus Resistance	Non-nutrient

¹Application life refers to the length of time that mixed compound remains at a consistency suitable for application with spatula or caulking gun. Application life is always measured at a standard temperature of 77°F with a relative humidity level of 50%. In general, for every 20°F rise in temperature, the application life is halved; and for every 20°F drop, it is doubled. High humidity levels during the mixing process will shorten application life.

²Tack-free time is the length of time after which a mixed sealant will no longer tightly adhere to L-LP-690 standard low density polyethylene film

³Cure time is defined as the length of time it takes AC-[®]615 Class B sealant to reach 30A hardness. It depends on three factors: remaining application life, temperature and relative humidity. To a certain extent, the temperature/humidity factors for application life also apply to curing. To accelerate the curing process, apply heat up to (but not more than) 120°F.



Mixing Instructions

Two-Part Sealant Cartridges:

1. Holding the cartridge, grasp the dasher rod and pull back approximately one inch.
2. Insert the ramrod into the hollow of the dasher rod, break the piston loose, and inject about 1/3 of the contents into the cartridge.

Note: Do not inject all of catalyst in one location. Distribute evenly throughout base material.

3. Repeat steps 2 and 3 until all the contents of the rod are emptied into the cartridge. Remove the ramrod.
4. Mix for the required number of strokes (hand mixing) or for the required amount of time (machine mixing) indicated in the kit instructions.
5. When mixing is complete, remove bottom cap.
6. Pull the dasher rod back to the neck of the cartridge, grasp the cartridge firmly at the neck, unscrew the dasher rod and remove.
7. Screw the nozzle into the cartridge, insert into the extrusion gun and use as required. For hand extrusion, press the used dasher rod against the plunger to force the material from the cartridge.

Storage

The shelf life of AC-®615 Class B sealant is 12 months from date of manufacture, when stored at temperatures below 80°F in its original container.

Mixed AC-®615 Class B may be stored under refrigeration as follows:

15 days at -10°F
30 days at -40°F

It is important to remember that freezing, storing and thawing procedures reduce application life. Also, frozen storage will reduce application life by varying amounts depending on the storage temperature and length of storage time. All aspects of storage, freezing and thawing should be planned carefully and it is not recommended to mix and freeze with less than ½ hour of available application time.

Health and Safety Precautions

AC-®615 Class B sealant is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Material Safety Data Sheet (MSDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An MSDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

All values are typical and are not intended for specification use.

AC-615B-09/09

AC- and AC TECH are trademarks of Advanced Chemistry & Technology, Inc. registered with the US Patent and Trademark Office
US Patent 6,486,268

Seller and manufacturer make no warranty, express or implied, concerning this product, or its merchantability or fitness for any purpose, except that the product conforms to manufacturer's product specifications during its applicable shelf life. User shall determine the suitability of this product for the intended purpose and method of application. Seller and manufacturer's only obligation shall be to replace the quantity of the product proved to be defective. AC TECH shall not be liable for damages in excess of the purchase price of this product.

Advanced Chemistry & Technology, Inc

7341 Anaconda Avenue Garden Grove, CA 92841 T: 714.373.2837 F: 714.373.1913

Page 2 of 2